

IV. AMENDMENTS TO THE CLAIMS

1. (Currently Amended) Inserting paper for glass-like sheet materials ~~comprised of~~ fabricated from glass, comprising:

a nonwoven sheet made of regenerated cellulose, wherein a content of hot water solubles in said nonwoven sheet is less than 0.1 wt%.

2. (Currently Amended) Inserting paper for glass-like sheet materials as set forth in claim 1, wherein said nonwoven sheet is formed without using a binder.

3. (Currently Amended) Inserting paper for glass-like sheet materials as set forth in claim 1 or 2, wherein said nonwoven sheet is pressed by a flat roller.

4. (Currently Amended) Inserting paper for glass-like sheet materials as set forth in claim 1 or 2, wherein said nonwoven sheet is supercalendered.

5. (Currently Amended) Inserting paper for glass-like sheet materials as set forth in claim 3, wherein said nonwoven sheet is supercalendered.

6. (Currently Amended) Inserting paper for glass-like sheet materials as set forth in claim 1 or 2, wherein a surface roughness of said nonwoven sheet is not more than 1.5 μm as measured by a KES-FB-4S surface tester.

7. (Currently Amended) Inserting paper for glass-like sheet materials as set forth in claim 3, wherein a surface roughness of said nonwoven sheet is not more than 1.5 μm as measured by a KES-FB-4S surface tester.

8. (Currently Amended) Inserting paper for ~~glass-like~~ sheet materials as set forth in claim 4, wherein a surface roughness of said nonwoven sheet is not more than 1.5 μm as measured by a KES-FB-4S surface tester.

9. (Currently Amended) Inserting paper for ~~glass-like~~ sheet materials as set forth in claim 5, wherein a surface roughness of said nonwoven sheet is not more than 1.5 μm as measured by a KES-FB-4S surface tester.